

## Tarp and Recreation Material

# 8207 MFRLTC

## Coated Polyester Mesh Material

Physical Property	Test Method	Imperial	Metric
Base Fabric	type	Polyester	
Base Fabric Weight	ASTM D751 Nominal	3.0 oz/ yd <sup>2</sup>	102 g/ m <sup>2</sup>
Weight	ASTM D751	7 oz/ yd <sup>2</sup> +3/-1 oz/ yd <sup>2</sup>	237 g/ m <sup>2</sup> +105/-35 g/ m <sup>2</sup>
Breaking Yield Strength	ASTM D751 Grab Tensile - Warp/Fill	230/200 lbf	1025/890 N
Strip Tensile	ASTM D 751 Procedure B - Warp/Fill	200/140 lbf/in	175/123 daN/5 cm
Low Temperature Resistance	ASTM D 2136 Low Temperature Bend 1/8" (3.2mm) mandrel, 4 hours	Pass @ -40° F	Pass @ -40° C
Flame Resistance	ASTM D5132 Horizontal Burning Rate	12 in/minute (max)	305 mm/minute (max)

Unless stated otherwise, values presented here represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.