

8028 Architectural Fabric

Minimum Specifications

Physical Property	Test Method	Imperial	Metric
Base Fabric	type	Polyester	
Base Fabric Weight	ASTM D751 (Nominal)	7.5 oz/ yd ²	250 g/ m ²
Finished Coated Weight	ASTM D751	28 oz/ yd ² +2/-1 oz/ yd ²	950 g/ m ² +70/-35 g/ m ²
NOTE: Weight of opaque/colored fabrics may be up to 4 oz/yd ² (140 g/m ²) heavier			
Tear Strength	ASTM D751 Trapezoid Tear - Warp/Fill	85/ 85 lbf	380/ 380 N
Breaking Yield Strength	ASTM D751 Procedure A Grab Tensile - Warp/Fill	700/ 700 lbf	3115/ 3115 N
Strip Tensile	ASTM D 751 Procedure B	515/ 515 lbf/ in	4500/ 4500 N/ 50mm
Adhesion	ASTM D 751 Dielectric Weld	10 lbf/ in	90 N/ 50 mm
Hydrostatic Resistance	ASTM D 751 Method A	500 psi	3.45 Mpa
Dead Load Seam Strength	ASTM D 751 4 hour test @ 160° F (71° C) 4 hour test @ 70° F (21° C)	266 lbf/ in 133lbf/ in	1180 N/ 25 mm 590 N/ 25 mm
Low Temperature Resistance	ASTM D 2136 Low Temperature Bend 1/8" (3.2 mm) mandrel, 4 hr	LTC LTA Pass @ -40° F Pass @ -67° F	Pass @ -40° C Pass @ -55° C
Flame Resistance	Meets NFPA 701, method 2 ULC-S109 ASTM 6413 - 2 second flameout Registered by California Fire Marshal (No. F-010301) ASTM E84 - flame spread index ≤25, smoke development rating ≤450 GB8624-2006 EN-13501-1: B-s2, d0		

Unless stated otherwise, values presented here represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.

8028 Architectural Fabric

Biaxial Stretch Test Results

