

Tarp Material

3810 MFRLTC

Lightweight Coated Polyester Material

Physical Property	Test Method	Imperial	Metric
Base Fabric	type	Polyester	
Base Fabric Weight	ASTM D751 Nominal	5.0 oz/ yd ²	170 g/ m ²
Weight	ASTM D751	10 oz/ yd ² +2/-1 oz/ yd ²	339 g/ m ² +70/-35 g/ m ²
Tear Strength	ASTM D751 Tongue Tear - Warp/Fill 8"(200mm)x10"(250mm) @ 12"/min(5mm/sec)	80/80 lbf	355/355N
Breaking Yield Strength	ASTM D751 Grab Tensile - Warp/Fill	350/300 lbf	1560/1335 N
Strip Tensile	ASTM D 751 Procedure B - Warp/Fill	300/275 lbf/in	2630/2410 N/50mm
Adhesion	ASTM D751 Dielectric Weld	7 lbf/ in	61 N/ 50 mm
Low Temperature Resistance	ASTM D 2136 Low Temperature Bend 1/8" (3.2mm) mandrel, 4 hours	Pass @ -40° F	Pass @ -40° C
Hydrostatic Resistance	ASTM D751 Procedure A	250 psi	1.72 MPa
Flame Resistance	ASTM D5132 Horizontal Burning Rate	6 in/minute (max)	152 mm/minute (max)

Unless stated otherwise, values presented here represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.