

## Tarp and Recreation Material

# 3522 MFRLTC/LTA

### High-Strength Coated Polyester Material

Physical Property	Test Method	Imperial	Metric
Base Fabric	type	Polyester	
Base Fabric Weight	ASTM D751 Nominal	6.0 oz/ yd <sup>2</sup>	203 g/ m <sup>2</sup>
Weight	ASTM D751	22 oz/ yd <sup>2</sup> +2/-1 oz/ yd <sup>2</sup>	746 g/ m <sup>2</sup> +70/-35 g/ m <sup>2</sup>
Tear Strength	ASTM D751 Tongue Tear - Warp/Fill 8"(200mm)x10"(250mm) @ 12"/min(5mm/sec)	150/150 lbf	670/670 N
Breaking Yield Strength	ASTM D751 Grab Tensile - Warp/Fill	450/450 lbf	2000/2000 N
Strip Tensile	ASTM D 751 Procedure B - Warp/Fill	325/300 lbf/in	2850/2630 N/50mm
Adhesion	ASTM D751 Dielectric Weld	10 lbf/ in	90 N/ 50 mm
Low Temperature Resistance	ASTM D 2136 Low Temperature Bend 1/8" (3.2mm) mandrel, 4 hours	LTC LTA Pass @ -40° F Pass @ -67 F	Pass @ -40° C Pass @ -55° FC
Hydrostatic Resistance	ASTM D751 Procedure A	500 psi	3.45 MPa
Flame Resistance	ASTM D5132 Horizontal Burning Rate	6 in/minute (max)	152 mm/minute (max)

Unless stated otherwise, values presented here represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.